



Mungo Befestigungs AG
 Bornfeldstr. 2
 4603 Olten
 Switzerland

Eurofins Product Testing A/S
 Smedeskovvej 38
 DK-8464 Galten
 Denmark

Tel. +45 70 22 42 76
 Fax +45 70 22 42 75
 voc@eurofins.dk
 www.eurofins.com/product-emissions

Date
 13 February 2013

Our ref.
 G17689-1B

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

Sample identification	MIT-SP
Product type	Construction Adhesive
Product data, according to manufacturer	Density: 1.77 g/ml at 20 °C ** Water content: 0.38% ** Exempt compounds: none ***
Date received	26 October 2012
Analytical period	November 2012

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U _m (%)
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

$$\left([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}] \right) / \left([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}] \right)$$

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk/uncertainty.

Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
MIT-SP	97.6	0.38**	0***	36	70*

* VOC limit for "Construction Adhesive"

** Given by the client

*** No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Thomas Neuhaus
 Head of product emission test centre